





Ag Nanopowder Datasheet

		NB-01	NB-02	NB-03	NB-04
Purity	%	> 99.8	> 99.5	> 99.5	> 99.5
Particle size D50	nm	35	20	50	80
Bulk density	g/ml	0.94	0.96	0.92	0.87
Specific surface area	m ² /g	10.4	10.88	10.1	9.5
Shape	—	Ball	Ball	Ball	Ball



NaBond Technologies Co., Limited

Address: B-204, Ding Tai Feng Hua, Qianhai Road Nanshan, Shenzhen, China 518052

Tel: 86-755-89801091

Fax: 86-755-86058970

<http://www.nabond.com>

email: info@nabond.com