


## Boron Nanopowder datasheet

Average particle size	10-50nm
Shape	amorphous
Purity	99.70%

### Impurities

Mg	0.0005
Al	0.022
Ca	0.0013
Ti	0.0017
Cr	0.013
Fe	0.035
Ni	0.004
Cu	0.0009
Cu	0.18
Si	0.01



NaBond Technologies Co., Limited

Address: B-204, Ding Tai Feng Hua, Qianhai Road Nanshan, Shenzhen, China 518052

Tel: 86-755-89801091

Fax: 86-755-86058970

<http://www.nabond.com>

email: [info@nabond.com](mailto:info@nabond.com)