

Co Nanopowder

Black gray powder

Purity >99.9%

Impurities	Si	Fe	Ni	Cr	Mn
Content	0.004%	0.01%	0.08%	0.0002%	0.003%

Average Particle Size: ≈28nm (0-60nm)

Special surface area: 40-60 m²/g

Saturation magnetization intensity: 1020.0 Km²/Kg (Sample: 0.41g; bulk density:0.48 g/cm³)

Intrinsic Coercive Force: 75.6 KA/m (Sample: 0.41g; bulk density: 0.48 g/cm³)

