


Molybdenum Nanopowder datasheet	
Appearance	purple powder
Average particle size:	$D_{50}=60\text{nm}$
Morphology:	Sphere
Purity:	>99.5 %
BET specific surface area:	10-8 m^2/g
Bulk density	0.24 g/cm^2
processing method	Physical Vapor Deposition



NaBond Technologies Co., Limited



Address: B-204, Ding Tai Feng Hua, Qianhai Road Nanshan, Shenzhen, China 518052

Tel: 86-755-89801091

Fax: 86-755-86058970

<http://www.nabond.com>

email: info@nabond.com



NaBond Technologies Co., Limited