


## Silicon Nano-powder datasheet

|                       |                         |
|-----------------------|-------------------------|
| Appearance            | Ochre powder            |
| Purity                | >99%                    |
| crystal form          | Polycrystalline         |
| average particle size | 100nm                   |
| specific surface area | 22m <sup>2</sup> /g     |
| apparent density      | 0.08g/cm <sup>3</sup>   |
| Zeta potential        | -18.5mV                 |
| processing method     | plasma vapor deposition |



NaBond Technologies Co., Limited


Address: B-204, Ding Tai Feng Hua, Qianhai Road Nanshan, Shenzhen, China 518052

Tel: 86-755-89801091

Fax: 86-755-86058970

<http://www.nabond.com>

email: info@nabond.com



## NaBond Technologies Co., Limited

---

Address: B-204, Ding Tai Feng Hua, Qianhai Road Nanshan, Shenzhen, China 518052

Tel: 86-755-89801091

Fax: 86-755-86058970

<http://www.nabond.com>

email: [info@nabond.com](mailto:info@nabond.com)