


Micrometer grade carbonyl Nickel powder NB-01

Average Size (μm)	2.2~3.6
Apparent Density (g/cm ³)	0.75~1.00
Shape	nearly sphere

Chemical Composition (%)	
Ni	Residue
Fe	≤ 0.03
C	≤ 0.15
O	≤ 0.25
S	≤ 0.001
Restimpurity	≤ 0.01

Chief use
metallurgical powder. magneto mat. contact mat. catalyst Cd-Ni cell raw mat.etc. Gas absorbent raw mat



NaBond Technologies Co., Limited

Address: B-204, Ding Tai Feng Hua, Qianhai Road Nanshan, Shenzhen, China 518052

Tel: 86-755-89801091

Fax: 86-755-86058970

<http://www.nabond.com>

email: info@nabond.com